



Polyester Sanding Primers

Black 2001 Gray 2090 White 2081 Neutral 20X2

GEL TIME: 16-20 min @ 77°
VISCOSITY: 1600 cps
COVERAGE (16-MILS): 100 sf/gal
THIX INDEX: 3.68
WEIGHT PER GAL: 11.3 lbs

FLASH POINT: 95° F
VOCs: 1.71 lbs/gal
MONOMER CONTENT: 20%
SHELF LIFE: 6 months @ 68° F
DUST FREE TIME: 45 min @ 77° F

product applications

- ✓ Metallic Primer – Automotive, Tanks
- ✓ In Mold Primer for Post Paint Application
- ✓ Pattern Surfaces – Tooling Board (Urethane, Epoxy)
- ✓ Wood Primer – MDF, Marine Grade Woods
- ✓ Marine Application
- ✓ Architectural Wood Surfaces

product features

- ✓ Quick build primer
- ✓ Quickly fills uneven surfaces and major imperfections
- ✓ Easy sanding prep for surface primer and top coats
- ✓ Low VOC Product
- ✓ Perfect primer for Prestec topcoats or any other surface coatings desired
- ✓ Relatively high build to 60 MILS
- ✓ Virtually no porosity

application suggestions

- ✓ Catalyze at 2% w/ MEKP initiator (0.5 oz/quart)
- ✓ Utilization of HVLP spray gun optimizes finish
- ✓ Air pressure 25-40 PSI
- ✓ Maintain 12-18" distance between gun and surface
- ✓ Optimum Temperature of 77°F
- ✓ Start with flash coat (2 MILS). Wait 2 min then start build coats of 4 MILS per pass, up to optimum 24 MILS.
- ✓ Can build to 60 MILS without sagging or cracking
- ✓ Allow full cure (24 hrs) prior to sand and polish or top coat application



info@CyrCACPC.com



www.CyrCACPC.com



909.923.2226



909.259.5000